# FACTS & FIGURES

#### SPECIFICATION DOCUMENT AND SAFETY DATA INFORMATION



## DURABELLA SEAMLESS TERRAZZO Declare.









#### **GENERAL**

Durabella is made out of various components based on a special modified binder, marble aggregates and/or natural stones. Durabella Biopolymer is made from vegetable oil and is Red List Free. Durabella is a flexible terrazzo and has a 40% better sound absorption compared to tradional epoxy terrazzo.

#### **FIELD OF APPLICATION**

Durabella Seamless Terrazzo is an aesthetic, seamless, wear-resistant finish for areas with heavy traffic. Suitable for both new construction and renovation (10-18mm) project. Durabella is therefore often used in public buildings such as shopping malls, hotels, receptions, restaurants, convention centers, airports, banks, offices, hospitals, entrance halls, stations, public areas, etc.

#### **LOOK AND FEEL**

Very similar to the traditional terrazzo floors. The surface is smooth. Various patterns and motifs can be obtained in the floor. In contrast to traditional terrazzo floors Durabella can be supplied in RAL, Pantone or NCS colors. The finish can be adjusted to your liking and color composition is customer specific. Slip-resistance is depending on the finish, R9 or R11.

#### **DESIGN**

Unlimited possibilities with the color of the binder and the mixing of the aggregates allowing designers to create their own visual. Aectual X Durabella is an innovative and sustainable flooring solution, created in collaboration with Aectual, combining 3D printed patterns with the Durabella. A novel take on classic artwork terrazzo flooring, offering endless design opportunities to integrate storytelling in your flooring design.

#### **CHARACTERISTICS**

Flexural Strength	Approx. 25 N/mm <sup>2</sup>
Compressive Strength	Approx. 40-60 N/ mm <sup>2</sup>
Adhesion Strength	> 3N/mm <sup>2</sup>
Tensile Strength	Approx. 30 N/mm <sup>2</sup>
Elongation at break	Approx. 120%
Binder	Biopolymer
Fire rating	Bfl S1 (EN 13501-1)
Color	Unlimited possibilities
Hardness	Shore D65
Thermal isolation	0,027 m <sup>2</sup> x K/W
Underfloor heating	Possible

- 100% UV stable
- Seamless
- Easy to clean and maintain
- Classic elegance
- Sound absorbing
- Chemical resistant
- Highly resistant to abrasion
- Can be used exterior
- Fast delivery times and high day production
- Can be laid on old surfaces
- Maximum strength and no hairline cracking
- Thickness from 8 to 15mm

#### **MAINTENANCE**

Regular removal of dust and if necessary wet cleaning with a neutral cleaning agent. For further instructions see the maintenance instruction quide.

#### HARDENING AND CURING

Durabella is ready for foot traffic at 15°C after 24 hours. The full hardening has occurred after 7 days assuming a temperature of 15°C. After curing the floor is ground to the desired surface. The floor is waxed or impregnated.



Duracryl International BV Elandstraat 91 2901 BK Capelle a/d IJssel The Netherlands +31 10 458 85 52 info@duracryl.com



Duracryl International GmbH Maybachstrasse 6 D 71397 Nellmersbach Germany +49 7195 59296-0 vertrieb@duracryl.com

















### DURABELLA SEAMLESS TERRAZZO







WANT TO KNOW MORE ABOUT THE PRODUCT? CLICK HERE!











in (s)









sales@duracryl.com

New York, NY 10001 United States of America +1(469) 243 4107

Duracryl International INC

350 Seventh Avenue, Suite 903

